



Quantum Timber Finishes Product Data Sheet

MicroClear



- Description:** MICROCLEAR IS A WATERBORNE OIL MODIFIED URETHANE ALKYD, DRYING TO A MEDIUM GLOSS FINISH WITH VERY LITTLE YELLOWING.
- MICROCLEAR IS A SINGLE PACK HARDWEARING WATER CLEAR, FAST DRYING COATING WITH A VERY SMOOTH FLOW AND SELF LEVELLING FINISH. IT IS TINTABLE, NON TOXIC, LOW ODOUR AND V.O.C. COMPLIANT.
- Also available in a satin finish.
- Available** Suitable for furniture, doors, windows, cupboards, storage units skirting boards.
- Application:** Interior timber surfaces must be fresh and clean. Apply by brush, short nap 8-9mm roller or spray. MicroClear causes very little grain raising on most wood, however de-nibbing first coat is recommended. MicroClear is fast drying; multiple coats per day are possible. Avoid using over 30 deg Celsius, one hour drying time between coats is advised. Sanding between coats is not usually required; however a light de-nibbing after first coat may be beneficial. After curing has taken place, surfaces may be cleaned with mild detergent and water.
- Coverage:** 10-16 square metres per litre. First coat can use a little more.
- Spraying:** Airless spray 313-315 tip, H.V.L.P. or air spray.
MicroClear can be reduced by 5% with water.
- Drying Time:** MicroClear is fast drying, touch dry in 30 minutes at 25°. Full hardness and cure will take 7 days @ 25 deg Celsius. Care should be taken with new surfaces.
- Tinting:** MicroClear can be tinted. Or used as an overcoat to Quantum Aquastain Colours.
- Disposal:** Do not pour left-over product down drain.
- Clean up:** Wash brushes and tools in soap and water.
- Disclaimer:** Recycled timber should always be tested prior to application on an off-cut or small patch out of sight. This test needs to be done for adhesion and over-coating.
- Environment:** Quantum Timber Finishes do not use mineral spirit products in manufacturing, hence all Quantum products are low in VOCs. **VOC <135g/litre**
- The entire range is free of hazardous air pollutants (HAPS).

Ph: 03 9776 8831

Fax: 03 9782 4417

Freecall: 1800 053 018

quantum@qtf.com.au